



2968-GA RV Roof Primer Clear / Blue

- Improves adhesion
- Extends life of roof coatings
- Ideal for silicone coatings

Gardner® RV Roof Primer is a high performance primer designed to provide exceptional adhesion and bonding strength for coatings applied to single ply membranes. It is highly recommended to use this product on most single ply surfaces prior to application of any type of protective, reflective or maintenance coating.

PREPARATION:

Surface must be pressure washed prior to primer application. Surfaces must be clean, dry, and sound; contaminants such as dirt, dust, grease, wax, oils, soap film, mold & mildew, bond breakers, curing compounds, and loose, peeling paint must be removed before priming or painting. Surfaces with mildew or stains must be cleaned prior to applying this product. Rinse thoroughly. Due to the wide variety of single ply membranes and raw materials used in their manufacturing process, always complete an adhesion peel test with Gardner RV Coating to determine if Gardner RV Roof Primer is needed. If primer is determined to be needed, use prior to patching and/or coating.

APPLICATION:

For exterior use only. Always apply on a clear, warm sunny day. Application should be completed a minimum of 4 hours prior to sunset. Temperatures must be between 30°F (-1°C) and 110°F (43°C) for 24 hours. Apply with brush, short nap exterior roller or sprayer. Apply a smooth and continuous coat over all areas. Must be cured a minimum of 4 - 8 hours before applying other coatings. Fully cures in 4 hours at 70°F & 50% relative humidity. Higher humidity, thicker films, poor air flow and lower temperatures will increase dry times. SPRAY INFO: 2000-3000 PSI, .030 - .041 Tip Size, 1-3 GPM.

COVERAGE: 1 quart per 125 sq. ft., per coat depending on surface type, texture, condition and porosity).

STORAGE & HANDLING PRECAUTIONS:

Do not store at temperatures below 30°F (-1°C) or above 110°F (43°C) and do not allow product to freeze. Keep closed when not in use.

LIMITED WARRANTY AND DISCLAIMER:

WARRANTY: Gardner-Gibson warrants to the original purchaser, contingent upon original proof of purchase, that this product will be free from any defects that may materially and adversely affect the product's performance for a period of one year from the date of original purchase.

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS:

Weight Per Gallon	9.98 lb.
Solids by Weight* (ASTM D1644)	10%
Solids by Volume* (ASTM D2697)	9%
Viscosity (ASTM D2697)	30 - 40 Ku
Adhesion to EPDM	8.3 - 12.5 lbs/in
Adhesion to TPO	6.0 - 8.5 lbs/in
Consistency	Brush, Roll, or Spray
Skin Time (50% Relative Humidity, 70 °F)	30 min.
Full Cure (50% Relative Humidity, 70 °F)	3 - 4 hrs.
Application Temperature	30°F and above
Spray Info	2000-3000 PSI .030-.041 Tip Size 1.0-3.0 GPM

*Note: Percentage may vary + or - 5%

Approx. Shipping Weights:

(Note: All approx. weights include container)

1 quart	3 lb.
---------	-------

VOC: <50 g/L max. (regulatory)

⚠ WARNING: This product can expose you to chemicals including cumene, which are known to the State of California to cause cancer, and toluene, which is known to the State of California to cause birth defects or other reproductive harm. For more information, go to www.P65Warnings.ca.gov