



5761-GA

RV Roof Coating

100% Silicone

- **Waterproofs in just one coat**
- **Withstands ponding water**
- **Rain safe in 15 minutes**
- **UV resistant**
- **Lowers roof temperatures**

Gardner® RV Roof Coating is a 100% silicone, extremely reflective roof coating for flat roofs or areas where ponding water may occur. The high solids, low odor formula sets quick, will not crack and can be applied in a wide temperature range. Gardner RV Roof Coating exceeds performance requirements of ASTM D6694, ASTM D7281, Title 24 and CRCC rated.

PREPARATION:

All surfaces must be clean, dry, have proper drainage and free of surface rust, dust and any other foreign matter or debris. Rusty surfaces must be properly cleaned then primed. Mold or mildew stains must be cleaned with a compatible cleaner prior to application. It is recommended to perform an adhesion peel test prior to full application of Gardner® RV Roof Coating. Adhesion peel test instruction can be found at www.gardnercoatings.com/peel-test.

PRIME: Prime the entire roof surface (when needed) prior to patching and coating.

PATCH: Repair all leaks and cracks before applying any coating. Make repairs with Gardner RV Seam Tape or Gardner Silicone RV Leak Sealant. Allow repair to cure according to product directions before application of roof coating.

APPLICATION:

Mix well before applying. A power drill mixing tool is ideal. Confirm all dew or moisture has completely dried from the roof before applying. Best applied on a clear, dry day with warming temps between 35°F (1°C) and 120°F (48 °C). Use a quality, heavy duty 3/4" nap paint roller or professional airless sprayer. Gardner RV Roof Coating is a self-leveling, moisture-cured product that can be applied in one coat.

COVERAGE: Approximately 75 square feet per gallon

STORAGE & HANDLING PRECAUTIONS:

Do not heat or thin. Keep container sealed when not in use. Product must be kept out of sunlight, protected from the elements and in areas where air flows freely and is not restricted. Shelf life is up to 18 months from date of manufacturer for unopened containers. For maximum shelf life store between 50°F (10°C) and 80°F (26°C). Storage at temperatures outside these conditions or at relative humidity over 65% will reduce shelf life. Storage longer than 6 months may require additional mixing. Tightly seal container after opening and when not in use. Opened containers should be used within 3 - 5 days after opening. If a skin forms, remove prior to mixing material.

WARRANTY AND DISCLAIMER: Gardner-Gibson warrants product to be free of material defects for the lifetime of the existing roof, assuming it is in sound condition, from the date of purchase. Product must be applied in accordance with the proper application procedures, and for the intended use as stated on the label. Proper preparation and drying conditions must be observed to achieve correct results. Should a product not perform as stated, Gardner-Gibson shall, within its sole discretion and upon receipt of purchaser's timely written notice within the Warranty Period, provide replacement product to repair the affected area or prorate a portion of the purchase price of the defective product based on the claim period. This limited warranty does not cover labor or installation costs, consequential damages or incidental damages. Under no circumstances will the company be liable for any amount in excess of the product purchase price. Contact company below to request a refund with purchase receipt. There are no warranties which extend beyond the description on the face hereof. THIS LIMITED WARRANTY IS THE SOLE WARRANTY PROVIDED BY GARDNER-GIBSON TO THE PURCHASER. THERE IS NO IMPLIED WARRANTY OF MERCHANTABILITY OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE PROVIDED WITH THIS PRODUCT.

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS:

Solids Weight	97 ± 3%
Solids Volume	97 ± 3%
Viscosity	7,000 cps
Pounds per Gallon	11.05 ± 0.5 lb.
Hiding Power	98.38%
Gloss	78.60%
Tensile Strength	250 psi
Tear Resistance	37 lb/linear ft
Reflectivity	90 ± 1%
Emissivity	0.90
SRI value	115
Permeability	3 perms
Water Absorption	0.1%
Elongation	315%

Approx. Shipping Weights:

(Note: All approx. weights include container)

1 gallon (3.4L) 10.6 lb.

VOC: <10 g/L (regulatory)